



DRYWALL SPECIALTIES CORP.

FLAME – RESISTANT FIBERGLASS MESH SPECIFICATIONS

Weight (after coat):	4.5 oz/yd ² +/- 0.15 oz/yd ² (152g/m ² +/-5g/m ²)
Weight (before coat):	3.9 oz/yd ² +/- 0.06 oz/yd ² (132.2g/m ² +/-2g/m ²)
Mesh Size:	6 x 6 mesh/inch (4 x4mm)
Thickness:	0.0135 inches - .035 cm
Warp:	130 tex
Weft:	295 tex
Weave:	Leno
Resin Content:	14% +/-3%
Tensile Strength:	Warp 150 lbs/in (1300N/50mm) Weft 150 lbs/in (1300N/50mm)
Alkaline Resistance:	After 28-day immersion in 5% Na (OH) solution, the average retention rate for tensile fracture strength: 50%

Drywall Specialties Corp.
November 21, 2007