



## DRYWALL SPECIALTIES CORP.

### SELF-ADHESIVE DRYWALL MESH TAPE SPECIFICATIONS

Weight (after coat):	2.2 oz/yd <sup>2</sup> +/- 0.15 oz/yd <sup>2</sup> (75g/m <sup>2</sup> +/-5g/m <sup>2</sup> )
Weight (before coat):	1.6 oz/yd <sup>2</sup> +/- 0.06 oz/yd <sup>2</sup> (54g/m <sup>2</sup> +/-2g/m <sup>2</sup> )
Mesh Size:	9 x 9 mesh/inch (2.85 x2.85mm)
Warp:	32 tex
Weft:	90 tex
Resin Content:	28% +/-5%
Tensile Strength:	Warp 57 lbs/in (500N/50mm) Weft 86 lbs/in (750N/50mm)
Alkaline Resistance:	After 28-day immersion in 5% Na (OH) solution, the average retention rate for tensile fracture strength: 60%

Drywall Specialties Corp.  
November 21, 2007